



# Simulation Study of Perfect Dual Band Microwave Metasurface Absorber

Raed Ashraf Kamil Albadri<sup>1</sup>, Khalid Saeed Lateef Al-Badri<sup>2\*</sup>

## Abstract

This study presents analytical results using the CST software for a very simple design of an electromagnetic wave absorber with a negative refractive index, a copper circular-shape printed on an insulating layer separating it from a flat ground layer of copper. This design provides two absorption bands with an absorption capacity of 97.55%. This absorption is due to the dipole oscillation. Also, controlling the shape dimensions and thickness of the insulating layer leads to good results in the synthesis of the resonant frequency that contributes to the applications of energy collection and protection from the effects of electromagnetic waves. The results gave the highest value of absorption with dielectric thickness  $h = 0.5$  mm) and by selecting a proper the gap value for  $g = 0.3$  mm. It is also worth noting that the design can be developed to operate in a wide range of frequencies such as microwaves, terahertz, up to optical frequencies, which may contribute to potential applications in many engineering and optical technologies.

**Key Words:** Dual Band, Microwave, Optical Technologies.

**DOI Number:** 10.14704/nq.2022.20.3.NQ22055

**NeuroQuantology 2022; 20(3):160-165**

160

## Introduction

Metamaterials are materials with ideal properties in the spectrum of electromagnetic waves and with an infinitesimal cell size compared to the wavelength (Veselago, 1968), they have attention of scientists due to its special properties and due to potential applications such, Ideal lenses (Al-Badri et al, 2016), negative refractive index (Al-badri, 2019) back wave (Kern & Werner, 2003) split ring resonators (Al-badri & Lateef, 2020), nonlinear phenomena (Zhu et al, 2010) lattice structure (Al-Badri et al, 2018), perfect absorber (Rahmat-Samii & Mosallaei, 2001) cloaking (Chen et al, 2006), background waves (Al-Badri, 2021), and many more other structures have been suggested in the literatures to achieve materials with super electromagnetic properties (Dolling et al, 2005). Most of the structures proposed for metamaterials depend primarily on a metal resonator that fluctuates

greatly within the design frequency range with large energy losses that are never inevitable which negatively affect its performance. On the other hand, these losses play a fundamental role in optical frequencies.

The world witnessed the first perfect absorber in 2002 by Landy et al. (Landy et al, 2008), with an absorption capacity of 88%. It consisted of a separate loop and a separated wire by an insulating substrate (Abdulkarim et al, 2020). Also, in 2008, they demonstrated an ideal absorption of electromagnetic waves using a carefully engineered interconnected structure (Mahdi et al, 2021). Since then, ideal absorbers based on metallurgical material technology have received a large amount of attention, and numerous engineering designs have been proposed in this field (Schurig et al, 2006; Alici & Ozbay, 2007).

**Corresponding author:** Khalid Saeed Lateef Al-Badri

**Address:** <sup>1</sup>Department of Physics, University of Samarra, Samarra, Iraq; <sup>2\*</sup>Department of Physics, University of Samarra, Samarra, Iraq.

<sup>2\*</sup>E-mail: khalidsaeed@uosamarra.edu.iq

**Relevant conflicts of interest/financial disclosures:** The authors declare that the research was conducted in the absence of any commercial or financial relationships that could be construed as a potential conflict of interest.

**Received:** 02 January 2022 **Accepted:** 06 February 2022




This effort is due to its ability to achieve 100% absorption of electromagnetic waves due to its importance in many applications such as spectral detection, phase determination, thermal imaging, accurate thickness gauge, and solar cell applications. It is very difficult to find natural substances with an ideal absorption capacity to develop an absorber to generate a very high value in the terahertz frequency band. This absorber can be used in airport security systems, imaging systems, thermal detectors, and more (Li et al, 2016; Al-badri, 2020). The need for absorbers that operate in the microwave package increases due to the importance it carries in reducing interference in radars, collecting energy, using it in wireless charging, and hiding from detection in the military industries, sensors, and others. Great efforts have been made to achieve the ideal absorption of electromagnetic radiation in gigahertz limits. For example, (Landy et al, 2008) achieved a single beam absorbance with an absorption rate of 98%. Landy et al. (Landy et al, 2008) obtained an imperceptible absorption polarization with an absorption rate of 77%. In (Alici & Ozbay, 2007) showed a single absorption with a wide polarization angle. Unfortunately, all of these efforts share a weakness, which is the narrow width of the absorbed wave packet that greatly hinders practical applications. Later on, some methods were followed to develop the absorption beam or multiplexed absorption beam with gigahertz boundaries such as two- and three-beam absorbers (Al-Badri & Muhammad, 2020, Liu et al, 2015). Also, some efforts have worked on developing broadband absorbent materials by stacking multiple layers of metal resonators within a single cell (Zhang et al, 2008; Al-badri, 2020). However, in many cases, the narrow-band absorber is essential for spectroscopic imaging and sensors. Unfortunately, the absorption of narrow-band materials shares some disadvantages. First, the

absorption performance of the proposed design is sensitive to the polarization of incident waves that greatly impede scientific applications. Second, the uneven surface of the structures makes it very difficult to manufacture, especially at frequencies such as terahertz, infrared, and visible region. Finally, and most importantly, it is difficult to increase the absorption capacity (Peng et al, 2018). This study introduces a dual-beam absorber within a microwave frequency band. In many designs, a three-layer structure is adopted, with two metal layers separated from each other by electrical insulation. The shape and dimensions of the first metal layer are chosen according to the work requirements. The second metal layer is often in the form of a flat surface that prevents any transmission of the electromagnetic wave and reflects waves like a mirror at the same time. The design consists of a metal ring placed on an insulating layer separating it from the copper ground layer. The results showed the presence of two distinct absorption regions that reach a peak of more than 97%. The absorption mechanism of the dual absorbent consists of the interference of two different resonant frequencies. Additionally, the dimensions and design characteristics are controllable to expand the number of absorption zones to three or more.

**Design**

In this paper, an absorbent is designed as a copper of circular-shaped resonator separated from the ground layer by a type of insulation FR-4 with a thickness ( $h=0.5\text{mm}$ ). The value of the relative permittivity  $\epsilon_r=4.3$ . Figure (1) displays the vertical projection of one cell of the proposed design on which the details of the dimensions are fixed as shown in Table (1). It should be noted that the metal used is copper with a conductivity of  $5.8 \times 10^7 \text{ S/m}$ .




**Figure 1.** Proposed design (a) perspective view showing the dimensions of one cell, (b) a side view



**Table 1.** Dimensions details for the proposed design

Parameter	Value (mm)
$P_x$ (Unit cell width)	16
$P_y$ (Unit cell height)	16
$h$ (Unit cell thickness)	0.5
$r$ (circle radius)	7.5
$s$ (triangle length)	4.15
$g$ (gap width)	0.3

The design was analyzed using CST Microwave studio MWS software in the frequency band from 14 GHz to 19 GHz, assuming that the waveform is of the basic type TE<sub>10</sub>. The wave propagation vector  $k$  is along the direction of the  $z$ -axis, and the electric field vector  $E$  is parallel to the direction of the  $y$  axis, the magnetic field vector  $H$  is parallel to the  $x$ -axis, and the type of analysis used is (Frequency domain analyzing).




**Figure 2.** CST program settings

**Results**

After extracting the  $S$  values using the CST program, the absorption values for the frequency are calculated according to the equation (Kenney et al, 2017; Al-Badri, 2021):

$$A = 1 - R - T \quad (1)$$

Where the value of  $A$  represents the absorption coefficient,  $R$  represents the reflection coefficient, and  $T$  represents the permeability coefficient.



**Figure 3.** Shows the spectrum of absorption, reflection, and transmission of electromagnetic radiation

The design provides double absorption peaks; The first is at a frequency of 15.52 GHz and with an absorption rate of 99.93%, and the second at a frequency 17.26 GHz with absorption rate of 97.55% as shown in Figure (3), the simulated results present for the incident wave under normal incidence. Importantly, the incident wave has reflected with the unity magnitude  $R$  at two frequencies 15.52 GHz and 17.26 GHz, respectively. The absorption is perfect at these frequencies.

For further clarification, the effect of the thickness change of the substrate FR-4 on the absorption level (Figure 4) was studied. The results showed that the increase in the insulating substrate thickness leads to a nonlinear increase in the absorption level. The results show that the highest value of absorption with  $h = 0.5$  mm thickness of the substrate. Also, it can be noticed that the resonant frequency and frequency bandwidth decrease by increasing the dielectric substrate thickness. The results show that



the absorption are change by increasing the thickness of the substrate due to the higher substrate has to be compensated by increasing the loss component of the substrate.




Figure 4. The effect of change in the substrate thickness on absorption level

Negligible electric polarization effects are found in the change of azimuth angle, and therefore the change in phi angle cannot regulate the resonance frequency of this mode. However, the variation of

the phi could not change the absorption intensity therefore we can say this design electromagnetic polarization insensitive as shown in Figure (5).




Figure 5. The effect of the change in the electrical polarization angle on the absorption level

The results in Figure 5. shows that the absorption spectra do not change at different TE polarization angles, this due to the axisymmetric structure of the resonance unit cell. This indicates that the proposed metamaterial absorber is insensitive to TE polarization. This characteristic is very important in practical applications.

Figure 6 shows the simulated absorption, when the proposed design adopted the gap value of  $g=0.1$  mm,

0.3 mm, 0.5 mm and 0.7 mm. By adopting  $g$ , the absorption was improved obviously shifted from left to right for the two peaks. Hence, by selecting a proper value for  $g = 0.3$  mm, the proposed design obtained the good absorption results. The results of the absorption capacity and resonance frequency is change by increasing the gap between structure parts due to the higher electric coupling between metallic parts.






Figure 6. The effect of a change in the gap g on the absorption level

### Conclusion

The simulation results showed the possibility of producing an electromagnetic absorber with two perfect absorption bands as a metasurface structure with its simplicity of design and thinness. This design can be used in many scientific applications such as weather satellites, solar cells and reduce the effects of electromagnetic waves. However, the results of controlling the geometric dimensions of the design showed the possibility of obtaining more control over the absorption levels and the absorption frequency. The results showed the highest value of absorption with  $h = 0.5$  mm) and the proposed design obtained good absorption results by selecting a proper value for  $g = 0.3$  mm. It is also worth noting that the design can be modified to operate at a variety of frequencies, including microwaves, terahertz, and optical frequencies.

### References

- Veselago VG. The Electrodynamics of Substances with Simultaneously Negative Values of  $\epsilon$  and  $\mu$ . *Physics-Uspeski* 1968; 10(4): 509-514.
- Al-Badri KS, Cinar A, Kose U, Ertan O, Ekmekci E. Monochromatic tuning of absorption strength based on angle-dependent closed-ring resonator-type metamaterial absorber. *IEEE Antennas and Wireless Propagation Letters* 2016; 16: 1060-1063.
- Al-badri KSL. Multi band metamaterials absorber for stealth applications. *Revista Eletronica Gestao & Saude* 2019; 11(1): 133-144.
- Kern DJ, Werner DH. A genetic algorithm approach to the design of ultra-thin electromagnetic bandgap absorbers. *Microwave and Optical Technology Letters* 2003; 38(1): 61-64.
- Al-badri KSL, Lateef OS. Materials recognition based on electromagnetic metamaterial absorber. *In IOP Conference Series: Materials Science and Engineering* 2020: 928(7).
- Zhu B, Wang Z, Huang C, Feng Y, Zhao J, Jiang T. Polarization insensitive metamaterial absorber with wide incident angle. *Progress In Electromagnetics Research* 2010; 101: 231-239.
- Al-Badri KSL, Karacan N, Kucukoner EM, Ekmekci E. Sliding planar conjoined cut-wire-pairs: A novel approach for splitting and controlling the absorption spectra. *Journal of Applied Physics* 2018: 124(10).
- Rahmat-Samii Y, Mosallaei H. Electromagnetic band-gap structures: classification, characterization, and applications. *11th International Conference on Antennas and Propagation (ICAP 2001)* 2001: 560-564.
- Chen HT, Padilla WJ, Zide JM, Gossard AC, Taylor AJ, Averitt RD. Active terahertz metamaterial devices. *Nature* 2006; 444(7119): 597-600.
- Al-Badri KSL. Dual Band thin Metamaterial Perfect Absorber Based on Triangle Shape. *In Journal of Physics: Conference Series* 2021: 1818(1).
- Dolling G, Enkrich C, Wegener M, Zhou JF, Soukoulis CM, Linden S. Cut-wire pairs and plate pairs as magnetic atoms for optical metamaterials. *Optics letters* 2005; 30(23): 3198-3200.
- Abdulkarim YI, Deng L, Luo H, Huang S, Karaaslan M, Altıntaş O, Al-badri KSL. Design and study of a metamaterial based sensor for the application of liquid chemicals detection. *Journal of Materials Research and Technology* 2020; 9(5), 10291-10304.
- Mahdi WM, Al-Badri KSL, Alqaisi MR. Effect of Microwave Radiation on Bacteria, Fungi and Some Growth Characteristics of Cowpea *Vigna unguiculata* L. *Gesunde Pflanzen* 2021; 73(2): 161-167.
- Alici KB, Ozbay E. Electrically small split ring resonator antennas. *Journal of applied physics* 2007: 101(8).
- Schurig D, Mock JJ, Justice BJ, Cummer SA, Pendry JB, Starr AF, Smith DR. Metamaterial electromagnetic cloak at microwave frequencies. *Science* 2006; 314(5801): 977-980.
- Landy NI, Sajuyigbe S, Mock JJ, Smith DR, Padilla WJ. Perfect metamaterial absorber. *Physical review letters* 2008: 100(20).
- Galiffi E, Pendry JB, Huidobro PA. Broadband tunable THz absorption with singular graphene metasurfaces. *ACS nano* 2018; 12(2): 1006-1013.





- Al-Badri KSL, Muhammad FQ. Design and analysis quad-band patch antenna for wireless communication. *Samarra Journal of Pure and Applied Science* 2020; 2(1).
- Liu Y, Hao Y, Li K, Gong S. Radar cross section reduction of a microstrip antenna based on polarization conversion metamaterial. *IEEE Antennas and Wireless Propagation Letters* 2015; 15: 80-83.
- Zhang S, Genov DA, Wang Y, Liu M, Zhang X. Plasmon-induced transparency in metamaterials. *Physical review letters* 2008; 101(4).
- Al-badri KSL. Electromagnetic broad band absorber based on metamaterial and lumped resistance. *Journal of King Saud University-Science* 2020; 32(1): 501-506.
- Kenney M, Grant J, Shah YD, Escorcía-Carranza I, Humphreys M, Cumming DR. Octave-spanning broadband absorption of terahertz light using metasurface fractal-cross absorbers. *Acs Photonics* 2017; 4(10): 2604-2612.
- Muhammad FQ, Al-Badri KSL. Four band electromagnetic waves absorber using negative refractive index materials (metamaterials). *Scientific Journal of King Faisal University* 2020; 21(1): 1-11.
- Ji S, Jiang C, Zhao J, Zhang X, He Q. Design of a polarization-insensitive triple-band metamaterial absorber. *Optics Communications*, 2019; 432: 65-70.
- Al-Badri KSL. Design of perfect metamaterial absorber for microwave applications. *Wireless Personal Communications* 2021; 121(1): 879-886.
- Li SJ, Cao XY, Xu LM, Zhou LJ, Yang HH, Han JF, Zhao Y. Ultra-broadband reflective metamaterial with RCS reduction based on polarization convertor, information entropy theory and genetic optimization algorithm. *Scientific reports* 2016; 6(1): 1-12.
- Al-badri KSL. Ultrathin Perfect Metamaterial Absorber Based on Triquetra Shape. In *IOP Conference Series: Materials Science and Engineering* 2020: 928(7).
- Peng X, Ji J, Jing Y. Composite honeycomb metasurface panel for broadband sound absorption. *The Journal of the Acoustical Society of America* 2018; 144(4): EL255-EL261.
- Al-Fouadi AHA, Hussain RK. Synthesis and characterize of porous aluminum oxide nanoparticles. *NeuroQuantology* 2020; 18(1): 109-116.